

Current induced local spin polarization due to the spin-orbit coupling in a two dimensional narrow strip

Qian Wang, L. Sheng, and C. S. Ting¹

¹*Texas Center for Superconductivity, University of Houston, Houston, Texas 77204*

(Dated: today)

The current induced local spin polarization due to weak Rashba spin-orbit coupling in narrow strip is studied. In the presence of longitudinal charge current, local spin polarizations appear in the sample. The spin polarization perpendicular to the plane has opposite sign near the two edges. The in-plane spin polarization in the direction perpendicular to the sample edges also appears, but does not change sign across the sample. From our scaling analysis based on increasing the strip width, the out-of-plane spin polarization is important mainly in a system of mesoscopic size, and thus appears not to be associated with the spin-Hall effect in bulk samples.

In a spin-orbit coupled electron system, an external electric field can induce a transverse spin current, giving rise to the so-called spin Hall effect (SHE). The SHE may offer a new way to control electron spins in semiconductors, and so have potential applications in spintronic devices. Depending on its origin, the SHE is generally divided into two categories: the extrinsic SHE, which originates from spin-dependent electron anomalous scattering by impurities, and the intrinsic SHE, which occurs even in the absence of impurities. The extrinsic SHE, was first proposed by D'yakonov and V. I. Perel¹ in 1971 and reexamined recently by Hirsch² and Zhang³. The intrinsic SHE was predicted by Murakami, Nagaosa, and Zhang⁴ for p-type semiconductors and by Sinova et al.⁵ for n-type semiconductors in two-dimensional heterostructures. The intrinsic SHE has attracted much theoretical interests^{6,7,8,9,10,11,12,13,14,15,16,17,18}. Very recently, two independent groups have reported experimental evidence^{19,20} that an electric field can cause out-of-plane spin accumulations of opposite sign on opposite edges of semiconductor films, which is considered to be a signature of the SHE. Several analytical and numerical works have been published on the subject of spin accumulation in a semiconductor with spin-orbit coupling. Governale and Zülicke²¹ were the first to investigate spin accumulation. They studied the spin structure of electron states in a quantum wire with parabolic confining potential and strong Rashba spin-orbit coupling. Usaj and Balseiro²² showed that in a semi-infinite system with spin-orbit coupling, a current flowing parallel to the edge induces a net magnetization close to the edge. Using the Landauer-Büttik formula for a tight-binding model, Nikolić *et al.*²³ showed numerically that in a two-dimensional bar with a width of 30 lattice constant, the Rashba spin-orbit coupling can induce opposite spin accumulation near the two edges, which is qualitatively similar to that observed in the experiment. In order to clarify whether such spin polarizations are related to the SHE, it is important to investigate their scaling behavior with increasing sample size, and to reveal the parameters that control the relative magnitude of the spin accumulation or polarization.

In this paper, the electron wave function in a continu-

ous model is obtained for an infinite long conducting strip with finite width L . Using the Kubo formula, we show that a longitudinal electrical current induces both out-of-plane spin polarization (S_z) and in-plane spin polarization (S_y). Near the two edges, the spin polarization S_z has opposite sign, whereas S_y has the same sign. When sample width L increases, its scaling behavior indicates that S_z near the edges decreases and S_y becomes dominant for given fixed electrical current density. Therefore, the out-of-plane spin polarization is an effect due to boundary reflections from the two opposite edges, and appears not to be related to the SHE in a bulk sample.

Let us consider a system of a two-dimensional (2-D) infinite long conducting strip with finite width L . The Hamiltonian for the system with Rashba spin-orbit coupling can be written as by

$$H = \frac{k^2}{2m} + \lambda(\sigma_x k_y - \sigma_y k_x), \quad (1)$$

where λ is the coupling constant of spin-orbit interaction, σ_x and σ_y are the Pauli matrices, m is the electron effective mass, and we take units with $\hbar = 1$.

The eigenstates of plane waves are

$$|E_{\mp}, \vec{k}\rangle = |E_{\mp}, k_x, k_y\rangle = \frac{1}{\sqrt{2}} e^{i\vec{k}\cdot\vec{r}} \begin{pmatrix} \pm i e^{-i\phi} \\ 1 \end{pmatrix}, \quad (2)$$

where $\phi = \arctan(k_y/k_x)$, $+$ ($-$) labels lower (higher) energy eigenstate with eigenvalue $E_{\pm} = k^2/2m \mp \lambda k$ for a given $\vec{k}$.

Assuming hard-wall boundary conditions, the wave function at the two edges ($y = 0$ and $y = L$) is zero. Since the system is uniform along the x direction, k_x commutes with the Hamiltonian and is a good quantum number. We can write a eigenstate, with eigen-energy E , of the system as a superposition of four plane waves, with same E and k_x . Suppose the system is in universal region as defined in Ref. [5], the wave function near the Fermi level is given by

$$\begin{aligned} \Psi(E, k_x, y) &= |E, k_x\rangle \\ &= \alpha_{k_x} |E, k_x, k_y^- \rangle + \beta_{k_x} |E, k_x, -k_y^- \rangle \\ &\quad + \gamma_{k_x} |E, k_x, k_y^+ \rangle + \delta_{k_x} |E, k_x, -k_y^+ \rangle, \end{aligned} \quad (3)$$

where $k_y^\pm = \sqrt{k_x^2 - k_F^2}$ and $k^\pm = \pm \lambda m + \sqrt{\lambda^2 m^2 + 2mE}$ with boundary conditions $\Psi(k_x, 0) = \Psi(k_x, L) = 0$. One can solve the boundary conditions and find the eigenvalues of k_x , which are a discrete set of values in the interval of $(-k_F^+, k_F^+)$, here $k_F^+ = k_F$ with $E = E_F$ (the Fermi energy). In Usaj and Balseiro's work, there is only one edge, the eigenfunctions are propagating waves written as a superposition of one incident and two reflected waves. k_x can take any value between $(-k_F^+, k_F^+)$. In our current study, the interference due to the two edges of the strip limits number of eigenvalues for k_x at Fermi level, which could inject rather different physics for the problem.

While the four plane waves have different spin polarizations within the two-dimensional plane, their interference leads to nonzero out-of-plane local spin density. The local spin polarization depends on the sign of the conserved longitudinal wave vector k_x . For any given energy E and a positive eigenvalue k_{Enx} for k_x , $-k_{Enx}$ is also an eigenvalue for k_x . In the ground state where both positive and negative k_x states are occupied, the total local spin density is zero since the contribution of each spin band is zero. However, if there are a longitudinal current flow-

ing in the strip, which causes a small shift of the Fermi circles. The numbers of occupied states with positive k_x and negative k_x are no longer equal, which can induce net spin polarizations in the strip.

The net local spin polarization can be calculated using Kubo formula^{24,25},

$$\frac{\vec{S}(y)}{\mathcal{E}} = \frac{ie}{V} \sum_{k_x, E, E'} (f_{E'} - f_E) \times \frac{[\langle E', k_x | \frac{1}{2} \vec{\sigma}(y) | E, k_x \rangle \langle E, k_x | v_x | E', k_x \rangle]}{(E - E')(E - E' - i\delta)}. \quad (4)$$

where $\mathcal{E}$ is the electric field, and v_x is given by $v_x = k_x/m - \lambda\sigma_y$. Here, we wish to point out that the contribution to the spin polarization comes from the Fermi surface, in contrast to the intrinsic SHE, which comes from the contribution of all occupied states. It is easy to find that the spin polarization given by Eq (4) diverges in the clean limit. To overcome this problem, we consider a constant longitudinal current density I/L is driven through strip. We calculate the ratio between the spin polarization and the current density

$$\frac{\vec{S}(y)L}{I} = \frac{1}{e} \frac{\sum_{k_x, E, E'} [\langle E', k_x | \frac{1}{2} \vec{\sigma}(y) | E, k_x \rangle \langle E, k_x | v_x | E', k_x \rangle] \delta(E' - E) \delta(E - E_F)}{\sum_{k_x, E, E'} [\langle E', k_x | v_x | E, k_x \rangle \langle E, k_x | v_x | E', k_x \rangle] \delta(E' - E) \delta(E - E_F)}, \quad (5)$$

which is a finite quantity.

All the coefficients in Eq. 3 can be determined numerically. However, we found that the eigenfunctions (standing waves) can not be expressed as a superposition of the two eigenfunctions²² of same k_x obtained in the case of only one edge. We also found that, for $|k_x| < k_F^-$, $|\alpha| = |\beta|$ and $|\gamma| = |\delta|$; for $k_F^+ > |k_x| > k_F^-$, $|\gamma| = |\delta|$.

Plots in Fig. 1 show local spin polarizations $s_z = \frac{\hbar}{2} \langle E_F, k_x | \sigma_z | E_F, k_x \rangle$ and $s_y = \frac{\hbar}{2} \langle E_F, k_x | \sigma_y | E_F, k_x \rangle$ as functions of position y in all the eigenstates that have positive k_x with eigen-energy at the Fermi level for three different values of Rashba coupling λ , which is in the units of k_F . The width of the strip is set to be $8/k_F$, where k_F is the Fermi wave vector when there is no spin-orbit coupling. k_F is related to electron density in the sample by $k_F^2 = 2\pi n$. Using typical value of two-dimensional electron density 10^{12} cm^{-2} [see Ref. 26], we estimate $k_F \approx 10^8/m$ and L is around 80 nm. The spin polarizations s_z and s_y vanish at the two edges as required by the boundary conditions. For each eigenstate, $s_z(y) = -s_z(L - y)$, whereas $s_y(y) = s_y(L - y)$. We have also obtained s_x and it is zero across the sample. Without spin-orbit coupling, k_y is quantized to values $k_{yn} = n\pi/L$, where $n = 1, 2, 3, \dots$. For each k_{yn} , the eigenstates for two spin directions are degenerate. When spin-orbit coupling is in presence, the two spin bands

are no longer degenerate. However, the spin polarization increases as the Rashba coupling increases. When we further increase λ , some values of k_x are larger than Fermi wave vector of the higher spin band, as shown in Figs. 1(e) and (f). Under this case, decaying waves show up in the wave functions along the y-direction for the higher spin band.

The net spin polarizations are calculated by using the Kubo formula in Eq. (4). Figures 2(a), (c) and (e) show the net $S_z(y)L/I$ when we sum the contribution from all the positive k_x modes at the Fermi level. The longitudinal charge current also induces a local in-plane polarization S_y ^{8,23}, as shown in Figs. 2(b), (d) and (f), whereas $S_x \equiv 0$. Unlike S_z , S_y has the same sign across the sample. At weak Rashba couplings $\lambda = 0.01$ or 0.05 , we see from Figs. 2 (a)-(d) that S_z is one or two order greater than S_y in magnitude. With increasing the Rashba coupling, S_y increases much faster than S_z . As a consequence, S_y becomes comparable to S_z at relatively large Rashba coupling $\lambda = 0.1$, as seen from Figs. 2(e) and (f).

We have also obtained the local spin polarization for the case of $L = 16/k_F$. Figure 3 shows the results for $\lambda = 0.01, 0.05$, and 0.1 . There are 10 eigenvalues for k_x for each λ . Similarly to Fig. 2, the magnitude of spin polarization $S_z L/I$ near the edges increase as λ increases when λ is small. However, when λ is large ($\lambda = 0.1$),




FIG. 1: s_z [figure (a), (c), and (e)] and s_y [figure (b), (d), (f)] as function of position y for eigenvalues of positive k_x at the Fermi level. s_z and s_y are in units of $\frac{\hbar}{2}$. $L = 8/k_F$, where k_F is the Fermi wave vector when there is no spin-orbit coupling. For each of the three values of λ , there are 4 eigenvalues of k_x .




FIG. 2: Total local $S_z L/I$ and $S_y L/I$ as a function of y for $L = 8/k_F$. In this and following figures they are in units of $\hbar/(2ek_F^2)$. In (a) and (b) $\lambda = 0.01$. In (c) and (d), $\lambda = 0.05$. In (e) and (f), $\lambda = 0.1$.

magnitude of the polarization S_z near the edges becomes smaller and large oscillations appear deep inside of the sample. S_y also increases as λ increases. When $\lambda = 0.1$, in-plane spin polarization S_y dominates out-of-plane polarization S_z . Comparing with the results of $L = 8/k_F$, $S_z L/I$ is larger near the edges for $\lambda = 0.01$ and 0.05 . But when $\lambda = 0.1$, it is smaller. $S_y L/I$ is larger for all λ 's we chose. We conclude that for fixed finite sample size, the out-of-plane spin polarization S_z dominates at relatively weak Rashba coupling and in-plane spin polarization overwhelms for relatively strong Rashba coupling. It is interesting to examine how the spin polarization changes as the sample width L increases. In Fig. 4(a), we show $S_z L/I$ for various L with $\lambda = 0.05$. The peak magnitude of $S_z L/I$ near the $y=0$ edge increases as L increases at small L and decreases as L increases at large L . The plots for $\lambda = 0.1$ in Fig. 4(b) show a similar pattern, but the width, which has the biggest $S_z L/I$ near the edge, is shorter than that of $\lambda = 0.05$.

In summary, we showed that in a 2-D narrow semiconductor strip with weak Rashba spin-orbit coupling, local spin polarization could be induced by a steady longitudinal current, and it is originated from the wave functions





FIG. 3: Total local $S_z L/I$ and $S_y L/I$ as functions of y for $L = 16/k_F$. In (a), $\lambda = 0.01$. In (b), $\lambda = 0.05$. In (c), $\lambda = 0.1$.


of the electrons at the Fermi level. The charge current along the strip induces both out of plane and in plane local spin polarizations. Near the two edges, the spin polarization S_z has opposite sign, whereas S_y has the same sign. When the sample width L increases, the peak magnitude of $S_z L/I$ near the edges increases at small L and decreases at large L for weak λ . And at large L , our numerical results indicate that $S_y L/I$ becomes dominant. From our scaling analysis based on varying L , the out-of-plane spin polarization is important mainly in systems of mesoscopic sizes, and thus appears not to be associated with the SHE in bulk samples.

Acknowledgement-We wish to thank J. Sinova for helpful discussion. This work is supported by a grant from the Robert A. Welch Foundation and the Texas Center for Superconductivity at the University of Houston.

-
- ¹ M. I. D'yakonov and V. I. Perel', JETP Lett. **13**, 467 (1971).
 - ² J. E. Hirsch, Phys. Rev. Lett. **83**, 1834 (1999).
 - ³ S. C. Zhang, Phys. Rev. Lett. **85**, 393 (2000).
 - ⁴ S. Murakami, N. Nagaosa, S. C. Zhang, Science, **301**, 1348 (2003).
 - ⁵ J. Sinova et al., Phys. Rev. Lett. **92**, 126603 (2004).
 - ⁶ T. P. Pareek, Phys. Rev. Lett. **92**, 076601 (2004).
 - ⁷ Culcer *et al.*, Phys. Rev. Lett. **93**, 046602 (2004).
 - ⁸ E. G. Mishchenko, A. V. Shytov, and B. I. Halperin, Phys. Rev. Lett. **93**, 226602 (2004).
 - ⁹ J. I. Inoue, G. E. W. Bauer, and L. W. Molenkamp, Phys. Rev. B **70**, 041303 (2004).
 - ¹⁰ E. I. Rashba, Phys. Rev. B **68**, 241315 (2004); *ibid* **70**, 201309 (2004).
 - ¹¹ S. -Q. Shen, Phys. Rev. B **70**, R081311 (2004).
 - ¹² J. Schliemann and D. Loss, Phys. Rev. B **69**, 165315 (2004).
 - ¹³ S. Murakami, N. Nagaosa and S. C. Zhang, Phys. Rev. Lett. **93**, 156804 (2004).
 - ¹⁴ L. Sheng, D. N. Sheng and C. S. Ting, Phys. Rev. Lett. **94**, 016602 (2005).
 - ¹⁵ E. M. Hankiewicz, L. W. Molenkamp, T. Jungwirth, and J. Sinova, Phys. Rev. B **70**, 241301 (2004).
 - ¹⁶ B. K. Nikolić, L. P. Zârbo and S. Souma, cond-mat/0408693 (2004).
 - ¹⁷ S. Zhang and Z. Yang, Phys. Rev. Lett. **94**, 066602 (2005).
 - ¹⁸ K. Nomura *et al.*, Phys. Rev. B **71**, 041304 (2005).
 - ¹⁹ Y. K. Kato, R. C. Myers, A. C. Gossard, and D. D. Awschalom, Science **306**, 1910 (2004).
 - ²⁰ J. Wunderlich, B. Kästner, J. Sinova, T. Jungwirth, Phys. Rev. Lett. **94**, 127202 (2005).
 - ²¹ M. Governale and U. Zülicke, Phys. Rev. B **66**, 073311 (2002).
 - ²² G. Usaj and C. Balseiro, cond-mat/0405065
 - ²³ B. K. Nikolić, S. Souma, L. P. Zârbo, and J. Sinova, cond-mat/0412595.
 - ²⁴ R. Kubo, Can. J. Phys. **34**, 1274 (1956); J. Phys. Soc. Jpn. **12**, 570 (1957).
 - ²⁵ A. Crépieux and P. Bruno, Phys. Rev. B **64**, 014416 (2001).
 - ²⁶ J. Nitta, T. Akazaki, and H. Takayanagi, Phys. Rev. Lett. **78** 1335 (1997).



(a)



(b)

FIG. 4: Plots of $S_z(y)L/I$ for various L with $\lambda = 0.05$ [panel (a)] and 0.1 [panel (b)]. The value of L of each curve can be identified from the right end of the curve. In panel (a), $L=4,8,12,16,24$; in panel (b), $L=4,8,12,16,20$.